

exena.

QUANTUM S2 FO SR



DESCRIPTION	NORM EN ISO 20345:2022 + A1:2024	RESULT	REQUIREMENT
UPPER: Breathable Microfiber	5.4.3 Tear strength 5.4.6 Water vapor permeability Coefficient	160 N 1,2 mg/cm ² h 16,8mg/cm ²	≥60 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
VAMP LINING: Breathable, abrasion resistance.	5.5.2 Tear strength 5.5.3 Abrasion resistance (Wet) Abrasion resistance (Dry) 5.5.4 Water vapor permeability Coefficient	51 N No holes No holes 2,6 mg/cm ² h 22,3 mg/cm ²	≥ 15 N 25.600 cycles 51.200 cycles ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
QUARTER LINING: Breathable, abrasion resistance mesh	5.5.2 Tear strength 5.5.3 Abrasion resistance (Wet) Abrasion resistance (Dry) 5.5.4 Water vapor permeability Coefficient	35 N No holes No holes 80,6 mg/cm ² h 645,2 mg/cm ²	≥ 15 N 25.600 cycles 51.200 cycles ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
COUNTER LINING:	5.5.2 Tear strength 5.5.3 Abrasion resistance (Wet) Abrasion resistance (Dry) 5.5.4 Water vapor permeability Coefficient	33 N No holes No holes 15,2 mg/cm ² h 122,6 mg/cm ²	≥ 15 N 25.600 cycles 51.200 cycles ≥ 2,0 mg/(cm ² h) ≥20,0 mg/cm ²
SAFETY TOE CAP: Non-metallic, non-magnetic, 200 J	5.3.2.6 Impact resistance 5.3.2.7 Compression resistance	17,0 mm 20,7 mm	≥ 14 mm ≥ 14 mm

EXENA SRL
via Breda 20
62012 Civitanova M. MC
ITALY

REA MC144207
Reg. Impr. Trib. MC 01336080435
C.F. e P. IVA 01336080435
Cap. Soc. € 25.823,00 i.v.

+39 0733 89 72 56
info@exena.com
amministrazione@pec.exena.it

exena.com

exena.

FOOTBED: Removable,
cushioned, antistatic insole.

5.7.4.2 Abrasion resistance (dry)

NO HOLES

25.600 cycles

Abrasion resistance (wet)

NO HOLES

12.800 cycles

OUTSOLE : Dual-density
polyurethane

5.8.3 Tear strength

9 kN/m

≥ 8 kN/m

5.8.4 Abrasion resistance

36 mm³

≤ 150 mm³

5.8.5 Flexing resistance

0,3 mm

≤ 4,0 mm

5.8.6 Hydrolysis

0,1 mm

≤ 6,0 mm

6.4.2 Oils resistance

2 %

≤ 12%

6.2.10 Slip resistance on ceramic with
glycerin

0,32

≥ 0,19

(tilted towards the heel of 7°)

0,30

≥ 0,22

(tilted towards the tip of 7°)

5.3.5.2 Slip resistance on ceramic with
cleaning agent

0,37

≥ 0,31

(tilted towards the heel of 7°)

0,39

≥ 0,36

(tilted towards the tip of 7°)

6.2.2.2 Antistatic

dry: 32 MΩ

0,1 ÷ 1000 MΩ

wet: 5 MΩ

0,1 ÷ 1000 MΩ

SIZES: 34-48

WEIGHT:

34	35	36	37	38	39	40	41	42	43	44	45	46	47	48
637	675	713	751	789	827	865	903	941	979	1017	1055	1093	1131	1169

EXENA SRL

via Breda 20
62012 Civitanova M. MC
ITALY

REA MC144207

Reg. Impr. Trib. MC 01336080435
C.F. e P. IVA 01336080435
Cap. Soc. € 25.823,00 i.v.

+39 0733 89 72 56

info@exena.com

amministrazione@pec.exena.it

exena.com